

# COCOON 560™

## Constant Immersion Protection



Performance  
Coatings & Sealants  
Systems

### DESCRIPTION

COCOON 560 is formulated for protection of surfaces subject to constant immersion. It has maximum surface hardness and very high abrasion resistance. COCOON 560 is a liquid polyvinyl chloride coating which can be sprayed on any clean, dry building surface. Wherever it is sprayed, it forms a tough, strong, permanent waterproof skin that is adaptable to most interior surfaces. COCOON 560 is used in many situations including sludge dewatering areas, shower rooms, swimming pools, vehicle cleaning facilities, bottling plants, water cooling and recycling rooms, separators, and other areas where abrasion resistance, washability, moisture protection, chemical protection, fungi and bacteria resistance are important.

### OUTSTANDING FEATURES

- ✓ Attractive, jointless, hygienic seal that is highly resistant to impact and abrasion
- ✓ Maintains an effective seal against water and waterborne contaminants including chemical treatments and enzymes
- ✓ Maintains integrity of seals at pipe and duct penetrations, where expansion and contraction along dissimilar planes causes stress
- ✓ Resists abrasion from entrained solids of turbid wa-

ters in dynamic flow situations

- ✓ Low surface tension reduces drag coefficient at the surface/liquid interface
- ✓ Architectural colors available that maintain stability and definition in chemical environments

### APPLICATION

**CAUTION!** Read this entire data sheet before continuing. All surfaces must be dry, free of dirt, loose debris, oil, grease, or any substance that could interfere with adhesion. Additionally, all surfaces should be modified in a manner to make them as smooth as possible by removing sharp projections and filling gaps and voids. A minimum surface profile of 1/2 mm should be maintained for maximum adhesion. After proper masking, prime the entire surface to be

coated with Vinyl Bond B, directly from the can, by spray or roller, and allow the primer to dry. Close all penetrations through the surface by using a webbing coat. Webbing solution is made by mixing 1 part Webbing Agent with 3 parts Cocoon 560 and mix until the color is uniform. Spray apply the mixed Cocoon 560 in multiple overlapping passes until a 20 mil dry film thickness has been achieved. The first should be very light to avoid breaking the webs. Properly applied, the coating should be free of voids and pinholes. Voids and pinholes must be resprayed to achieve a complete seal. Prior to the removal of any protection or equipment, a thorough inspection of the entire area should be completed, and all damage or deficiencies must be repaired and resprayed. All termination joints should be sealed with a polyurethane sealant.

SPECIFICATIONS	
<b>Coating Type</b>	Polyvinyl Chloride Solution
<b>VOC</b>	252 gms/liter
<b>Pot Life</b>	Single Component
<b>Shelf Life</b>	12 months
<b>Recommended Thickness</b>	3 to 5 mils d.f.t. per coat
<b>Coverage</b>	1 gallon per 100 sq. ft. per coat x 4 coats
<b>Packaging</b>	5-gallon pails
<b>Colors</b>	Clear, White and other normal colors

# COCOON 560™

**Waterproof Protective Coating**



For recommendations regarding equipment, contact our Technical Department.

**LIMITATIONS**

Proper ventilation must be provided during application for effective drying of the coating, and all applicators must wear suitable respirators.

**MAINTENANCE**

Damaged areas may be repaired by cleaning surface and application of Cocoon 560 as described in the Application

section.

**PRECAUTIONS**

Read and understand the Material Safety Data Sheet thoroughly. Make sure that all involved parties are familiar with the M.S.D.S. Cocoon 560, in its liquid state, is flammable; and proper safety precautions against exposure to open flame, sparks, or other sources of ignition must be taken and strict safety rules enforced.

TECHNICAL DATA		
<b>Moisture Vapor Transmission</b>	0.06 perms	ASTM E-96
<b>Tensile Strength</b>	1100 psi	ASTM D-412
<b>Elongation</b>	150%	ASTM D-412
<b>Flexibility at Low Temperature</b>	180 deg. bend @ -30°C	ASTM C-711
<b>Flashpoint</b>	+0°F	FTMS 141A(M4293)
<b>Shore 'A' Hardness</b>	85	ASTM D-2240
<b>Total Solids</b>	30% (B.W.); 25% (B.V.)	ASTM D-1044
<b>Viscosity</b>	55 ku	ASTM D-446
<b>Drying Time</b>	5 minutes per coat	
<b>Fire Resistance</b>	Self-extinguishing	ASTM D-568-56T
<b>Cleaning of Equipment</b>	M.E.K. or Acetone	
<b>Weatherometer (240 hours)</b>	85 gloss	ASTM G-23

NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.

Effective Date: 04/2007

© 2007 Andek Corporation. All right reserved. ANDEK is a registered trademark